

CERAKOTE

CTC-997 PU HQ

HIGH QUALITY PU
for bathtub reconditioning



B01/rev2/CTC998/19052016/OMP

CTC-997 PU HQ

PRIMER

| | |
|-----------------|-------------------------|
| Name of product | : Cerakote CTP - 980 WB |
| Color | : White |
| Gloss Level | : Semi gloss |
| Shelf life | : 12 months |

APPLICATION DATA

| | |
|--------------------------|--|
| Substrate recommended | : Ceramic tiles, clinker, Terazzo, natural stone & glass surface |
| Condition recommended | : 10 - 35° C and 60 - 80% RH |
| Mixing ratio (by weight) | : Comp. A : Comp. B = 4 : 1 Recommended |
| Thinner for spraying | : Clean Water |
| Pot Life | : 30 minutes (30° C) |
| Coverage | : 8 - 10 m ² / kg - set per coat |
| Min wet film thickness | : 70 - 85 mic WFT 65 - 75 mic DFT |

TOP COAT

| | |
|-------------|--|
| Type | : Two component aliphatic acrylic polyurethane |
| Color | : White |
| Gloss Level | : Glossy |
| Shelf life | : 12 months |

APPLICATION DATA

| | |
|--------------------------|---|
| Substrate recommended | : Bathtub, ceramic tiles |
| Condition recommended | : 10 - 40° C and 60 - 80% RH |
| Mixing ratio (by volume) | : Comp. A : Comp. B = 2 : 1 Recommended |
| Thinner for spraying | : PU Thinner |
| Pot Life | : 60 minutes (30° C) |
| Coverage | : 3 - 4 m ² / L - set |
| Min wet film thickness | : 180 - 200 mic WFT 90 - 110 mic DFT |



Untuk informasi lebih lanjut, hubungi :
For further information, please contact us :

PROPAN INSPIRATION CENTER : ■ JAKARTA : ■ Satria : Phone : (+62 21) 5680081, 5680082, Fax.: (+62 21) 5680153 | PROPAN SANDIMAS HOME CENTER : ■ DENPASAR : Phone : (+62 361) 8495080, Fax.: (+62 361) 419247 | PROPAN SERVICE CENTER : ■ BANDUNG : ■ Soekarno Hatta : Phone : (+62 22) 7507776, Fax.: (+62 22) 7500775 ■ BALIKPAPAN : Phone : (+62 542) 7212410, 7212411, Fax.: (+62 542) 7212064 ■ BANJARMASIN : Phone : (+62 511) 4229655, Fax.: (+62 511) 4229559 ■ BATAM : Telp.: (+62 778) 466438, Fax.: (+62 778) 7418769 ■ BEKASI : Phone : (+62 21) 88851727, 88851728, Fax.: (+62 21) 8842070 ■ BOGOR : Phone : (+62 251) 8652599, Fax.: (+62 251) 8653079 ■ CIREBON : Phone : (+62 231) 231825, Fax.: (+62 231) 237616 ■ DENPASAR : Phone/Fax.: (+62 361) 8495088 ■ JAKARTA : ■ Kelapa Gading : Phone : (+62 21) 4516377, 4516379, Fax.: (+62 21) 4517007 ■ Fatmawati : Phone : (+62 21) 7237851, 7237854, Fax.: (+62 21) 7237855 ■ JEPARA : Phone : (+62 291) 594372, 3319372, Fax.: (+62 291) 594372 ■ LAMPUNG : Phone : (+62 721) 704491, Fax.: (+62 721) 771001 ■ MAKASSAR : Phone : (+62 411) 8111036, Fax.: (+62 411) 8111037 ■ MANADO : Phone/Fax.: (+62 431) 8880585 ■ PALEMBANG : Phone : (+62 711) 715360, 715361, 5480083, Fax.: (+62 711) 715362 ■ PONTIANAK : Phone : (+62 561) 6598896, Fax.: (+62 561) 6598894 ■ SAMARINDA : Phone : (+62 541) 7074750, Fax.: (+62 541) 744293 ■ SEMARANG : Phone/Fax.: (+62 24) 3581023 ■ SURABAYA : ■ Darmo : Phone : (+62 31) 5684855, 5616828, Fax.: (+62 31) 5623622 ■ RMI : Phone : (+62 31) 5043536, 5041237, Fax.: (+62 31) 5055071 ■ YOGYAKARTA : Phone : (+62 274) 871044 ■ E-mail : info@propanraya.com ■ website : ■ www.propanraya.com ■ f@PropanRayaCC ■ propanraya

DISTRIBUTOR : ■ BRUNEI DARUSSALAM, HIAP GUAN Sdn. Bhd : Phone: +673-2429020 / 2427266, Fax.: +673-242 1653 ■ MALAYSIA, SYN TAI HUNG TRADING Sdn. Bhd : Phone : +603-2287 9221 / 2287 5218, Fax.: +603-22879225 ■ MALAYSIA, ALKANA MALAYSIA. Sdn. Bhd: Phone : +603-5162 5789 / 91 / 63, Fax.: +603-5162 5742 ■ PHILIPPINES, SPURWAY ENTERPRISES : Phone : +632-413 7124 / 26, Fax.: +632-7274128 ■ MALDIVES, MAZIYA SERVICE Pvt Ltd : Phone : +960-3336729 / 3326169, Fax.: +960-3336728 ■ THAILAND, ADISAK TRADING Co. Ltd. : Phone : +66-76-261 420-6, Fax.: +66-76-261 427 ■ SINGAPORE, PAINTMART Pte. Ltd : Phone : +65-6848 0746, Fax.: +65 6841 4172 ■ VIETNAM, ALKANA, Thu Dau Mot City : Phone : +084-0650 3635 330, Fax.: +84-0650 3635 339

Brochure no.01/CTC-998/DRI



Sebelum
Before



Sesudah
After

CERAKOTE CTC - 997 PU HQ

Merupakan cat dari seri produk CERAKOTE yang didesign khusus untuk merekondisi bathtub tua / dekil menjadi baru kembali.

CERAKOTE CTC - 997 PU HQ

Is a paint series from CERAKOTE product which is special design for old bathtub reconditioning to become new bathtub.

Karakteristik Produk / Product Feature :

1. Cat Polyurethane 2K Kualitas terbaik
High quality 2K Polyurethane Topping
2. Lapisan film tebal dengan penampilan sangat menarik
High build film with excellent appearance
3. Tidak menguning
Non Yellowing
4. Mudah merata, bisa dikuas
Good flow, brushable
5. Mudah diaplikasikan
Easy to apply

Manfaat Produk / Product Benefit :

1. Sangat efektif dan efisien untuk merekondisi bathtub tua dan dekil
Very effective and efficient for bathtub reconditioning
2. Tahan bahan kimia pembersih, detergen, sabun dll
Excellent cleaning chemical resistance, detergent & soap resistance
3. Mempunyai daya kilap yang tahan lama.
Long time gloss retention
4. Daya tahan gores yang sangat baik
Excellent scratch resistance
5. Mudah dibersihkan
Easy to clean

Tahap Pembersihan / Preparation

Bersihkan bathtub yang akan di cat dari kerak kotoran, jamur, dll sampai betul-betul bersih kemudian amplas menggunakan kertas amplas no:#240 - 400, tergantung kotoran yang melekat. Pengecatan pada bathtub metal harus bersih dari karat terlebih dahulu kemudian lapis dengan menggunakan cat epoxy anti karat (zynchromate / zincphosphate).

Clean bathtub to be painted from dirt, crust, fungus and other contaminants, sand thoroughly with sand paper Nr:#240 - 400, depend on substrate condition. For metal bathtub, must be clean the surface from rust then apply anti corrosion paint (zynchromate / zincphosphate).



1

Tahap Cat Dasar / Primer Coat

- Campurkan satu set cat primer coat (CERAKOTE CTP - 980 WB) dengan **perbandingan berat** komp. A : komp. B = 4 : 1. Untuk aplikasi menggunakan spray gun dapat diencerkan dengan air bersih sekitar ±5 %. Aduk hingga merata, campuran secukupnya karena campuran ini akan mengeras dalam 60 menit.
*Mix one set of primer coat (CERAKOTE CTP-980 WB) with mixing ratio **by weight** comp. A : comp. B = 4 : 1. For application using spray gun, add clean water ±5%. Stir until homogeneous, mix as needed. The mixture will harden in 60 minutes.*

*Mix one set of primer coat (CERAKOTE CTP-980 WB) with mixing ratio **by weight** comp. A : comp. B = 4 : 1. For application using spray gun, add clean water ±5%. Stir until homogeneous, mix as needed. The mixture will harden in 60 minutes.*

- Semprotkan campuran cat tersebut dengan menggunakan spray gun, cukup sekali lapis sampai merata.
Apply mixed material with spray gun, just a single layer with good spreading and sufficient thickness as needed.

Apply mixed material with spray gun, just a single layer with good spreading and sufficient thickness as needed.

- Bila kondisi substrat (bathtub) cat lama masih bagus, tidak ada yang terkelupas (hanya sudah kusam), maka dapat langsung dilakukan pengecatan top coat dengan menggunakan CERAKOTE CTC - 997 PU HQ.
If the existing bathtub still good, just the painting doesn't look shiny, apply directly with CERAKOTE CTC - 997 PU HQ.

If the existing bathtub still good, just the painting doesn't look shiny, apply directly with CERAKOTE CTC - 997 PU HQ.



2



Tahap Cat Finish / Top Coat

- Setelah cat dasar (CERAKOTE CTP - 980 WB) biarkan kering 6 - 8 jam, dapat segera dilakukan pengecatan top coat dengan terlebih dahulu melakukan pengamplasan menggunakan kertas amplas yang halus no. #400, dengan tujuan untuk menghilangkan kotoran / debu yang menempel pada cat dasar saat cat belum kering. Kemudian bersihkan debu - debu bekas amplas tersebut.
After based coat (CERAKOTE CTP - 980 WB) allow to dry and cure for 6 - 8 hours), sand thoroughly with sand paper Nr. #400 and then clean the surface from dirt and other contaminant before apply top coat CERAKOTE CTC - 997 PU HQ.

After based coat (CERAKOTE CTP - 980 WB) allow to dry and cure for 6 - 8 hours), sand thoroughly with sand paper Nr. #400 and then clean the surface from dirt and other contaminant before apply top coat CERAKOTE CTC - 997 PU HQ.

- Campurkan satu set CERAKOTE CTC - 997 PU HQ dengan **perbandingan Volume** komp. A : komp. B = 2 : 1, encerkan dengan menggunakan thinner PU sekitar 10 - 20%, aduk hingga merata.
*Mixed one set of CERAKOTE CTC - 997 PU HQ with mixing ratio **by Volume** comp. A : comp. B = 2 : 1, add Polyurethane thinner (PU) 10 - 20%, stir until homogeneous.*

- Kemudian semprotkan ke substrat / bathtub yang akan di cat, untuk hasil yang lebih bagus gunakanlah spray gun jenis HVLP (High Volume Low Pressure). Untuk top coat dapat dilakukan dengan satu kali lapis saja dengan cara menyemprot secara merata dan agak tebal. Daya sebar sekitar 3 - 4 m²/ L - set.
Apply mixed material using spray gun. For best result using HVLP Spray gun (High Volume Low Pressure). For the top coat can be applied just a single layer with good spreading and sufficient thickness as needed. Coverage is 3 - 4 m²/ L - set.

Apply mixed material using spray gun. For best result using HVLP Spray gun (High Volume Low Pressure). For the top coat can be applied just a single layer with good spreading and sufficient thickness as needed. Coverage is 3 - 4 m²/ L - set.



3

