

PU CLEAR COAT PCR-8800 TURBO CLEAR GLOSS

No. TD : P-058
 Revision : 00
 Effective Date : 20/04/2022

PU CLEAR COAT PCR-8800 Turbo Fast Dry is 2K PU acrylic clear coat that specially designed for fast dry high quality repairs (express-technology). It can be polished after 20 min at 60 °C or after 2 hours air dry (at 30 °C). This product is suited for spot-repairs, owing excellent gloss and gloss retention against UV-light; also yellowing resistant. It could be thinned up to maximum 20 % with Thinner PU Medium or Fast Dry.

PRODUCT SPESIFICATION

Type	: 2K PU acrylic polyol	
Appearance	: Clear Liquid	
	<u>A Component</u>	<u>B Component</u>
	PCR-8800 Turbo	PCR PCRH-8800 Turbo
Solid content (NV, w/w)	: 42 ± 2 %	68 ± 2 %
Viscosity (Din Cup 4, 30°C)	: 20 ± 5 sec	14 ± 2 sec (Din Cup 4, 30°C)
Specific Gravity	: 0.96 ± 0.02 g/cc	1.06 ± 0.02 g/cc
Flash Point	: 36.6°C	36.6°C
Packing	: 0.8 L in steel can	0.2 L in steel can

APPLICATION

Application condition	: 25 - 30°C, 40 - 60% RH
Application method	: Spray
Thinning ratio	: 80 : 20 : 20 max (A : B : Thinner by volume)
Thinner	: Thinner PU Medium/Slow Dry (PU Grade)
Application viscosity (NK 2, 30°C)	: 11 - 13 sec
Pot life	: 1 - 2 hrs
Theoretical Coverage	: 4 - 5 m ² /L

FILM PROPERTIES

Drying Time	
▪ Surface dry	: 5 minutes (30°, Air Dry)
▪ Hard dry	: 2 hours (30°, Air Dry)
▪ Full cure	: 4 days (30°, Air Dry)
Gloss level (60 angle)	: > 90 %

OTHERS

Shelf life	: Two years if stored in cool and dry condition on original sealed can.
Storage and handling	: Keep away from heat and direct sunlight.

SURFACE PREPARATION

The surface must be clean, dry, and free from rust, oil, grease, and other contaminants with appropriate method.

APPLICATION INFORMATION

1. A and B component and Thinner should be mixed properly and stir thoroughly with agitator.
2. Close cap of B component tightly after use.
3. Apply by spray an even coat at coating amount 100 - 120 g/m².
4. Good ventilation in working area is suggested.

SAFETY PRECAUTION

1. This product contains aromatic solvent. It does not contain formaldehyde or heavy metals. Avoid contact with the skin and eyes. Wear suitable protective clothing such as working suit, goggles, masks, and safety gloves. Use barrier cream.
2. This product is flammable. Keep away from fire and direct sunlight. Use only explosion proof equipment. Do not breathe the vapor of spray.

FIRST AID:

- Eye contact : Rinse immediately with plenty of water for at least 15 minutes; seek medical advice.
- Skin contact : Wash with soap and water. If irritation occurs, seek medical advice.
- Ingestion : Provide symptomatic treatment and seek medical advice.
- Inhalation : Remove person to fresh air. Keep patient rested and give artificial respiration.

DISCLAIMER

This document contains information issued based on the best and latest of Propan's knowledge in accordance to laboratory testing and practical application experience. The end user must test the product's suitability for their specific application and purpose. Propan shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements. This document is subjected to change without further notice. Please consult Propan for any specific guidance on the suitability of this product for their needs or for any specific application practices.