

## DUROGLOSS PP PRIMER

No. TD : D-039  
Revision : 00  
Effective Date : 02/12/2019

**DUROGLOSS PP PRIMER** is a high quality acrylic 1K etching primer specially designed for polypropylene (PP) substrate. It is strongly recommended to finishing PP plastic part of motorcycle and car body in order to get excellent adhesion. This product supports any kind of finishing system in car body work and or refinish, both 1K and 2K.

### PRODUCT SPESIFICATION

Type	: Acrylic Based
Appearance	: Clear Liquid
Color	: Slightly Yellowish
Solid content by weight	: < 5 %
Viscosity	: 6 – 8 sec. D4
Specific gravity	: 0.86 ± 0.02 g/cc
Packing	: 1 Lt in steel can

### APPLICATION

Thinner	: N/A (ready to use)
Application method	: Spray
Thinning ratio	: N/A
Application viscosity	: 6 - 8 sec DIN 4
Surface dry	: ~ 5 minutes
Recoating time	: 5 minutes
Usage	: approx 1 liter for 9 m <sup>2</sup> at a film thickness of 10 microns

### SURFACE PREPARATION

The surface must be clean, dry, and free from rust, oil, grease, and other contaminants with appropriate method.

### APPLICATION CONDITION

Temperature	: 20 - 50°C
Humidity	: 80% RH

Provide adequate ventilation during application and drying

### SAFETY PRECAUTION

Avoid contact with the skin and eyes. Wear suitable protective clothing such as overalls, goggles, respirator, and solvent resistance gloves.

This product is flammable. Subject to spontaneous heating. Do not smoke. Use only explosion proof equipment. Do not breathe the vapor of spray. Ensure adequate ventilation and fresh air entry during application and drying. If there are experiences eye watering, headaches, dizziness or difficulty breathing, leave the area to obtain fresh air or respiratory protection.

**FIRST AID:**

- Eye contact : Rinse immediately with plenty of water for at least 15 minutes; seek medical advice.
- Skin contact : Wash with soap and water. If irritation occurs, seek medical advice.
- Ingestion : Provide symptomatic treatment and seek medical advice.
- Inhalation : Remove person to fresh air. Keep patient rested and give artificial respiration.